

## **SECTION 035413 - GYPSUM CEMENT UNDERLAYMENT**

### **PART 1 - GENERAL**

#### **1.1 SUMMARY**

- A. Section Includes: Self-leveling, gypsum cement underlayment for application below interior floor coverings.

#### **1.2 PREINSTALLATION MEETINGS**

- A. Preinstallation Conference: Conduct conference at Project site.

#### **1.3 ACTION SUBMITTALS**

- A. Product Data: For each type of product.

#### **1.4 QUALITY ASSURANCE**

- A. Installer Qualifications: Installer who is approved by manufacturer for application of underlayment products required for this Project.

#### **1.5 FIELD CONDITIONS**

- A. Environmental Limitations: Comply with manufacturer's written instructions for substrate temperature, ventilation, ambient temperature and humidity, and other conditions affecting underlayment performance.
  - 1. Place gypsum cement underlayments only when ambient temperature and temperature of substrates are between 50 and 80 deg F (10 and 27 deg C).

### **PART 2 - PRODUCTS**

#### **2.1 PERFORMANCE REQUIREMENTS**

- A. Fire-Resistance Ratings: Comply with ASTM E 119; testing by a qualified testing agency. Identify products with appropriate markings of applicable testing agency.
  - 1. Indicate design designations from UL's "Fire Resistance Directory" or from the listings of another qualified testing agency.
- B. STC-Rated Assemblies: For STC-rated assemblies, provide materials and construction identical to those tested in assembly indicated, according to ASTM E 90 and classified according to ASTM E 413 by an independent testing agency.
- C. IIC-Rated Assemblies: For IIC-rated assemblies, provide materials and construction identical to those tested in assembly indicated, according to ASTM E 492 and classified according to ASTM E 989 by an independent testing agency.

#### **2.2 GYPSUM CEMENT UNDERLAYMENTS**

- A. Gypsum Cement Underlayment: Self-leveling, gypsum cement product that can be applied in minimum uniform thickness of 1/8 inch (3 mm) and that can be feathered at edges to match adjacent floor elevations.

1. Basis-of-Design Product: Subject to compliance with requirements, provide Maxxon Corporation; Dura-Cap® or comparable products by one of the following:
    - a. ARDEX Americas.
    - b. MAPEI Corporation.
    - c. United States Gypsum Company.
  2. Cement Binder: Gypsum or blended gypsum cement as defined by ASTM C 219.
  3. Compressive Strength: Not less than 2500 psi at 28 days when tested according to ASTM C 109/C 109M.
  4. Underlayment Additive: Resilient-emulsion product of underlayment manufacturer, formulated for use with underlayment when applied to substrate and conditions indicated.
- B. Aggregate: Well-graded, washed gravel, 1/8 to 1/4 inch (3 to 6 mm); or coarse sand as recommended by underlayment manufacturer.
1. Provide aggregate when recommended in writing by underlayment manufacturer for underlayment thickness required.
- C. Water: Potable and at a temperature of not more than 70 deg F (21 deg C).
- D. Reinforcement: For underlayment applied to wood substrates, provide galvanized metal lath or other corrosion-resistant reinforcement recommended in writing by underlayment manufacturer.
- E. Primer: Product of underlayment manufacturer recommended in writing for substrate, conditions, and application indicated.
- F. Surface Sealer: Designed to reduce porosity as recommended by manufacturer for type of floor covering to be applied to underlayment.
- 2.3 ACCESSORIES
- A. Sound Mat: Manufacturer's standard sheet product with core of fused entangled filaments attached to non-woven fabric.
1. Basis-of-Design Product: Subject to compliance with requirements, provide Maxxon Corporation; Acousti-Mat II.
  2. Thickness: 1/4 inch.

## PART 3 - EXECUTION

### 3.1 PREPARATION

- A. General: Prepare and clean substrate according to manufacturer's written instructions.
1. Treat nonmoving substrate cracks according to manufacturer's written instructions to prevent cracks from telegraphing (reflecting) through underlayment.
  2. Fill substrate voids to prevent underlayment from leaking.
- B. Concrete Substrates: Mechanically remove, according to manufacturer's written instructions, laitance, glaze, efflorescence, curing compounds, form-release agents, dust, dirt, grease, oil, and other contaminants that might impair underlayment bond.

1. Moisture Testing: Perform anhydrous calcium chloride test, ASTM F 1869. Proceed with installation only after substrates do not exceed a maximum moisture-vapor-emission rate of 3 lb of water/1000 sq. ft. (1.36 kg of water/100 sq. m) in 24 hours.
- C. Wood Substrates: Mechanically fasten loose boards and panels to eliminate substrate movement and squeaks. Sand to remove coatings that might impair underlayment bond and remove sanding dust.
  1. Install underlayment reinforcement recommended in writing by manufacturer.
- D. Adhesion Tests: After substrate preparation, test substrate for adhesion with underlayment according to manufacturer's written instructions.
- E. Sound Control Mat: Install sound control materials according to manufacturer's written instructions.
  1. Do not install mechanical fasteners that penetrate through the sound control materials.

### 3.2 APPLICATION

- A. General: Mix and apply underlayment components according to manufacturer's written instructions.
  1. Close areas to traffic during underlayment application and for time period after application recommended in writing by manufacturer.
  2. Coordinate application of components to provide optimum adhesion to substrate and between coats.
  3. At substrate expansion, isolation, and other moving joints, allow joint of same width to continue through underlayment.
- B. Apply primer over prepared substrate at manufacturer's recommended spreading rate.
- C. Apply underlayment to produce uniform, level surface.
  1. Apply a final layer without aggregate to product surface.
  2. Feather edges to match adjacent floor elevations.
- D. Cure underlayment according to manufacturer's written instructions. Prevent contamination during application and curing processes.
- E. Do not install floor coverings over underlayment until after time period recommended in writing by underlayment manufacturer.
- F. Apply surface sealer at rate recommended by manufacturer.
- G. Remove and replace underlayment areas that evidence lack of bond with substrate, including areas that emit a "hollow" sound when tapped.

### 3.3 PROTECTION

- A. Protect underlayment from concentrated and rolling loads for remainder of construction period.

END OF SECTION